Thermoelectric Properties of Partially Double-filled $(\text{Ce}_{1-z}\text{Nd}_z)_y\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ Skutterudites

Ye-Eun Cha and Il-Ho Kim*

Department of Materials Science and Engineering, Korea National University of Transportation, Chungju 27469, Republic of Korea

Abstract: $(\text{Ce}_{1-z}\text{Nd}_z)_y\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ skutterudites were prepared by encapsulated melting, annealing, and hot pressing. The formation of a marcasite phase (FeSb_2) was significantly suppressed by partially filling the voids with Ce/Nd and making a Co substitution at the Fe site. Both the Hall and the Seebeck coefficient values were positive, indicating that all specimens had p-type characteristics. The electrical conductivity decreased with increasing temperatures, as in a degenerate semiconductor. The Seebeck coefficient increased with the charge compensation of Co and filler content of Nd; however, the electrical conductivity decreased. The partially double-filled specimens had a higher electrical conductivity and lower Seebeck coefficient than the completely double-filled specimens, due to the increase in carrier concentration. The lattice thermal conductivity was expected to decrease via partial double filling with Ce and Nd; however, it did not change significantly because of the comparable atomic masses and ionic radii of Ce and Nd. Therefore, the partially double-filled specimens had lattice thermal conductivities comparable to those of the completely double-filled ones. Co substitution had an influence on the ZT values due to the change in the intrinsic conduction onset temperature, which decreased with increasing Co content. Thus, the $(\text{Ce}_{1-z}\text{Nd}_z)_y\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ skutterudites are a promising material for thermoelectric power generation in the mid-to-low temperature regions.

(Received March 14, 2018; Accepted April 23, 2018)

Keywords: thermoelectric, skutterudite, partial double filling, charge compensation

1. INTRODUCTION

Skutterudite has a body-centered cubic structure (space group: $\text{Im}\bar{3}$) with a framework of 8MX_3 (M: Fe, Ru, Os, Co, Rh, Ir, Ni, Pd, and Pt, and X: P, As, and Sb) and two voids per unit cell. If the voids are filled with specific atoms (fillers or rattlers), the rattling effect of the fillers can greatly reduce the lattice thermal conductivity and thus improve the thermoelectric performance [1,2]. This skutterudite is called a filled skutterudite and, in general, the chemical formula RM_4X_{12} (R: alkali, alkaline-earth, and rare-earth elements) is used. $\text{RCo}_4\text{Sb}_{12}$ -based materials have been actively investigated for n-type filled skutterudites [3-5] and $\text{RFe}_4\text{Sb}_{12}$ -based materials have been examined for p-type filled skutterudites [6-8].

$\text{RCo}_4\text{Sb}_{12}$ has 72 valence electron counts (VEC) but $\text{RFe}_4\text{Sb}_{12}$ has only 68 VEC, and thus needs additional electrons for charge compensation [9]. Therefore, to optimize the carrier concentration, substitutions such as Co or Ni for the Fe sites are required, in addition to filling the voids with R atoms.

Void filling is a very effective method for improving the thermoelectric performance of p-type skutterudites. The lattice thermal conductivity is reduced, by the fillers, which act as phonon scattering centers of a specific resonance frequency [4,6,10,11]. Using rare-earth elements with heavier atomic masses as fillers can reduce the lattice thermal conductivities by phonon scatterings of lower frequencies, and using two or more filler elements can broaden the range of scattering frequencies [4,5,7]. Therefore, when double or multiple filling with two or more fillers is performed, it is expected that the lattice thermal conductivity can be further reduced due to the enhanced phonon scattering and in this way the thermoelectric

*Corresponding Author: Il-Ho Kim
[Tel: +82-43-841-5387, E-mail: ihkim@ut.ac.kr]
Copyright © The Korean Institute of Metals and Materials

performance can be improved [5,11-13]. It has recently been reported that Co- and Ni-substituted p-type filled skutterudites are not completely filled [14-16]. In our previous study, Ce/Nd-double-filled and Co-substituted skutterudites with $y = 1$ produced $(\text{Ce,Nd})\text{Sb}_2$ phases because the Ce/Nd double filling exceeded the filling fraction limit [17]. In the present study, partially Ce/Nd-double-filled and Co-substituted $(\text{Ce}_{1-z}\text{Nd}_z)_y\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ skutterudites were prepared and their phase, microstructure, charge transport, and thermoelectric properties were examined.

2. EXPERIMENTAL PROCEDURE

$(\text{Ce}_{1-z}\text{Nd}_z)_y\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ ($z = 0.25$ or 0.75 , $y = 0.8$, and $x = 0, 0.5$ or 1) skutterudites were synthesized by encapsulated melting. Elemental Ce (purity 99.9%, Sigma Aldrich), Nd (purity 99.9%, Kojundo), Fe (purity 99.95%, Cerac), Co (purity 99.95%, Alfa Aesar), and Sb (purity 99.999%, LTS) were melted at 1323 K for 10 h in an evacuated quartz tube coated on the inside with carbon and they were then quenched in water. The quenched ingot was annealed at 873 K for 24 h to homogenize the skutterudite phase. The annealed ingot was ground to a fine powder with a particle size of less than 75 μm , and then, the powder was hot pressed in a graphite die with an internal diameter of 10 mm at 898 K under 70 MPa for 1 h in a vacuum.

An X-ray diffractometer (XRD, Bruker, D8-Advance) was used for phase analysis of the hot-pressed specimens. $\text{Cu-K}\alpha$ (40 kV and 30 mA) radiation was used and the diffraction patterns were measured in the θ - 2θ mode ($2\theta = 10^\circ$ – 90°) with a scan speed of 0.4 sec/step, step size 0.02° , and wavelength 0.15405 nm. The microstructure was observed using a scanning electron microscope (SEM, FEI, Quanta400) and the chemical composition was analyzed by energy-dispersive spectroscopy (EDS, Bruker, Quantax200). The hot-pressed specimens were cut into rectangular pieces of $3 \times 3 \times 9 \text{ mm}^3$ to measure both the Seebeck coefficient (α) and electrical conductivity (σ), and then they were cut into discs with dimensions of 10 mm

(diameter) $\times$ 1 mm (thickness) to determine their thermal conductivity (κ). Charge transport properties such as the Hall coefficient (R_H), and carrier concentration (p) and mobility (m) were measured using a Keithley 7065 system at room temperature, with a constant magnetic field (1 T) and current (50 mA). The Seebeck coefficient and the electrical conductivity were measured with the ZEM-3 (Ulvac-Riko) equipment in a He atmosphere, and the thermal conductivity ($\kappa = Dc_p d$) was evaluated by measuring the thermal diffusivity (D), specific heat (c_p), and density (d) using the laser flash method with the TC-9000H (Ulvac-Riko) instrument, under vacuum. The electrical and thermal conductivities, the power factor ($\text{PF} = \alpha^2 \sigma$) and the dimensionless figure of merit ($ZT = \alpha^2 \sigma T \kappa^{-1}$) were studied using the measured Seebeck coefficient.

3. RESULTS AND DISCUSSION

Figure 1 shows the XRD patterns of the $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ skutterudites. Diffraction peaks corresponded to the standard data for the skutterudite phase (ICDD PDF# 56-1123); a small amount of the marcasite (FeSb_2) phase (ICDD PDF# 70-3985) was also identified. As shown in Fig. 1(b) and 1(c), peak intensity decreased with increasing Co content, and the formation of the marcasite phase was suppressed by the void filling and charge compensation. The diffraction peaks shifted to higher angles with increasing Co content, which indicated that the lattice constant decreased because the atomic radius of Co (0.167 nm) was smaller than that of Fe (0.172 nm).

Figure 2 represents SEM images and EDS line scans of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. The FeSb_2 phase (dark region) was observed with the skutterudite phase (bright region) in all specimens; however, the formation of the FeSb_2 phase was inhibited by the increasing Co content. This behavior was consistent with the XRD results. Song *et al.* [17] observed $(\text{Ce,Nd})\text{Sb}_2$ phases in the completely filled $\text{Ce}_{1-z}\text{Nd}_z\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$; however, in the present study, $(\text{Ce,Nd})\text{Sb}_2$ phases were not produced in the partially filled $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ because the partial filling

Fig. 1. (a) XRD patterns of the $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ skutterudites and enlarged diffraction peaks of the specimens with (b) $z = 0.25$ and (c) $z = 0.75$.

of the specimen did not exceed the filling fraction limit.

Table 1 shows the chemical composition and lattice constants of the $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. All specimens showed a density of over 98% of the theoretical density. Actual compositions showed slight differences from nominal compositions, possibly due to the oxidation of Ce and Nd and the volatilization of Sb during the synthesis and consolidation processes at high temperatures. The calculated lattice constants ranged from 0.9100 to 0.9127 nm, depending on the Ce/Nd filling ratio and Co substitution amount, and decreased with increasing Co content. However, there was almost no difference in the lattice constant with the variation in the Ce/Nd filling ratio, despite the difference in ionic radius between Ce (0.134 nm) and Nd (0.127 nm). In general, the lattice constant increases with increasing filling fraction, within the filling fraction limit. However, in the present study, all specimens with $y = 0.8$ reached the filling fraction limit; thus, the total filling fraction for each specimen was identical and, therefore, the change in the lattice constant with the variation of the Ce/Nd filling ratio was negligible.

The charge transport properties of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_4$.

Fig. 2. SEM images and EDS analyses of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$: (a) $(\text{Ce}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_4\text{Sb}_{12}$, (b) $(\text{Ce}_{0.25}\text{Nd}_{0.75})_{0.8}\text{Fe}_4\text{Sb}_{12}$, (c) $(\text{Ce}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$, (d) $(\text{Ce}_{0.25}\text{Nd}_{0.75})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$, (e) $(\text{Ce}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$, and (f) $(\text{Ce}_{0.25}\text{Nd}_{0.75})_{0.8}\text{Fe}_3\text{CoSb}_{12}$.

Table 1. Relative density, lattice constant, and transport properties of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ at room temperature.

Composition		Relative Density [%]	Lattice Constant [nm]	Hall Coefficient [$10^{-3} \text{ cm}^3 \text{ C}^{-1}$]	Carrier Mobility [$\text{cm}^2 \text{ V}^{-1} \text{ s}^{-1}$]	Carrier Concentration [10^{21} cm^{-3}]
Nominal	Actual					
$(\text{Ce}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_4\text{Sb}_{12}$	$\text{Ce}_{0.56}\text{Nd}_{0.18}\text{Fe}_{4.10}\text{Sb}_{11.96}$	99.97	0.9127	1.37	3.89	4.56
$(\text{Ce}_{0.25}\text{Nd}_{0.75})_{0.8}\text{Fe}_4\text{Sb}_{12}$	$\text{Ce}_{0.19}\text{Nd}_{0.55}\text{Fe}_{4.11}\text{Sb}_{11.95}$	99.23	0.9127	1.51	3.95	4.10
$(\text{Ce}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$	$\text{Ce}_{0.57}\text{Nd}_{0.19}\text{Fe}_{3.58}\text{Co}_{0.49}\text{Sb}_{11.97}$	98.96	0.9112	1.81	4.14	3.44
$(\text{Ce}_{0.25}\text{Nd}_{0.75})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$	$\text{Ce}_{0.19}\text{Nd}_{0.54}\text{Fe}_{3.58}\text{Co}_{0.52}\text{Sb}_{11.97}$	99.07	0.9116	2.48	4.94	2.52
$(\text{Ce}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$	$\text{Ce}_{0.57}\text{Nd}_{0.18}\text{Fe}_{3.04}\text{Co}_{1.06}\text{Sb}_{11.95}$	97.96	0.9100	3.95	5.55	1.58
$(\text{Ce}_{0.25}\text{Nd}_{0.75})_{0.8}\text{Fe}_3\text{CoSb}_{12}$	$\text{Ce}_{0.6}\text{Nd}_{0.53}\text{Fe}_{3.09}\text{Co}_{1.08}\text{Sb}_{11.94}$	99.04	0.9103	3.39	5.11	1.84

$x\text{Co}_x\text{Sb}_{12}$ at room temperature are shown in Table 1. All specimens exhibited positive signs of Hall coefficient, confirming that the majority carrier is a hole of a p-type semiconductor. As the amount of Co substitution increased, the carrier concentration decreased, because electrons were supplied by the charge compensation of Co to Fe. The carrier concentration changed slightly with the Ce/Nd filling ratio. The partially filled specimens ($y = 0.8$ and $x = 0-0.5$) showed higher carrier concentrations, ranging from 1.58×10^{21} to $4.56 \times 10^{21} \text{ cm}^{-3}$, while the completely filled specimens ($y = 1$ and $x = 0-0.5$) had values in the range of 1.29×10^{21} to $2.82 \times 10^{21} \text{ cm}^{-3}$ [17]. This difference results from the increase in carrier concentration due to electron shortage.

Figure 3 presents the temperature dependence of the electrical conductivity of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. The electrical conductivities slightly decreased with increasing temperature, indicating that the specimens were degenerate semiconductors. The electrical conductivity decreased with increasing Co content due to the increased carrier concentration. In addition, higher electrical conductivity was obtained in specimens where the filling fraction of Ce was higher than that of Nd. This was consistent with the carrier concentration change shown in Table 1. The electrical conductivities of the partially filled specimens ranged from 1.51×10^5 to $2.84 \times 10^5 \text{ Sm}^{-1}$ at 323 K, and were higher than those (1.53×10^5 to $2.05 \times 10^5 \text{ Sm}^{-1}$ at 323 K) of the completely filled specimens [17].

Figure 4 shows the temperature dependence of the Seebeck coefficient of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. Like

Fig. 3. Temperature dependence of the electrical conductivity of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. **Fig. 4.** Temperature dependence of the Seebeck coefficient of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$.

the Hall coefficient values listed in Table 1, the positive sign of the Seebeck coefficient implies p-type

Fig. 5. Temperature dependence of the power factor of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$.

conduction. The Seebeck coefficient increased with temperature and the Co-substituted specimens showed a maximum at 823 K due to intrinsic conduction. In addition, the Seebeck coefficient increased with increasing Co content. The Seebeck coefficient is inversely proportional to the carrier concentration and is expressed as $\alpha = (8/3)\pi^2 k_B^2 m^* T e^{-1} h^{-1} (\pi/3n)^{2/3}$, where k_B is the Boltzmann constant, m^* is the effective carrier mass, T is the absolute temperature, e is the electronic charge, h is the Planck constant, and n is the carrier concentration. Therefore, as the Nd filling and the Co substitution increased, the carrier (hole) concentration decreased and the Seebeck coefficient increased. $(\text{Ce}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$ showed a maximum Seebeck coefficient of $157.7 \mu\text{VK}^{-1}$ at 823 K while $\text{Ce}_{0.25}\text{Nd}_{0.75}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$ showed $160.2 \mu\text{VK}^{-1}$ at 723 K [17]. A comparison of the maximum Seebeck coefficients showed that the partially filled specimens exhibited lower values than the completely filled ones. This was because the carrier concentrations of the partially filled specimens were higher than those of the completely filled ones.

Figure 5 presents the variation of the power factor (PF) for $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. The Seebeck coefficient and the electrical conductivity have a trade-off relation which can be expressed as $\text{PF} = \alpha^2 \sigma$. Because both depend on the carrier concentration, the

Fig. 6. Temperature dependence of the thermal conductivity of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$: (a) total thermal conductivity, (b) electronic thermal conductivity, and (c) lattice thermal conductivity.

specimen with an optimum carrier concentration exhibits a maximum PF value. The maximum PF values were obtained for the Co-substituted ($x = 0.5$) specimens with higher Ce filling and for non-substituted ($x = 0$) specimens with higher Nd filling. Partial filling resulted in improved PF values due to the increased electrical conductivity, thus $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ showed PF values of 2.63 to $3.29 \text{ mWm}^{-1}\text{K}^{-2}$ at 823 K while $\text{Ce}_{1-z}\text{Nd}_z\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ showed PF values of 2.32 to $3.14 \text{ mWm}^{-1}\text{K}^{-2}$ at 823 K [17].

Figure 6 shows the temperature dependence of the thermal conductivity of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. As shown in Fig. 6(a), the partially filled specimens showed thermal conductivities ranging from 2.00 to $2.81 \text{ Wm}^{-1}\text{K}^{-1}$ at 323 K, which slightly increased above 723 K due to bipolar conduction. The thermal conductivity (κ) is expressed as the sum of the lattice thermal conductivity (κ_L) and the electronic thermal conductivity (κ_E). The κ_E value can be calculated from the Wiedemann-Franz law ($\kappa_E = L\sigma T$), where L is the Lorenz number, taken, for this study, as $2.0 \times 10^{-8} \text{ V}^2 \text{ K}^{-2}$. The calculated κ_E values are presented in Fig. 6 (b). $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_4\text{Sb}_{12}$ showed higher κ_E values (1.68 to $3.23 \text{ Wm}^{-1}\text{K}^{-1}$) than those of $\text{Ce}_{1-z}\text{Nd}_z\text{Fe}_4\text{Sb}_{12}$ (1.00 to $2.22 \text{ Wm}^{-1}\text{K}^{-1}$) [17]. This behavior results from the higher carrier concentration of $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_4\text{Sb}_{12}$ and the presence of the marcasite, which has higher electrical and thermal conductivities than the skutterudite [17]. However, $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_3\text{CoSb}_{12}$ exhibited relatively low κ_E values of $0.91 \text{ Wm}^{-1}\text{K}^{-1}$ to $2.09 \text{ Wm}^{-1}\text{K}^{-1}$ due to low carrier concentration and stable skutterudite phases. The separated κ_L values are shown in Fig. 6(c). $(\text{Ce}_{1-z}\text{Nd}_z)_{0.8}\text{Fe}_x\text{Co}_{1-x}\text{Sb}_{12}$ exhibited very low κ_L values of 0.12 to $1.14 \text{ Wm}^{-1}\text{K}^{-1}$ at all temperatures. To reduce the lattice thermal conductivity of the p-type single-filled skutterudites, low-resonance frequency scattering by fillers with heavy atomic masses and small ionic radii, which enhance phonon scattering, is effective [11,18]. The lattice thermal conductivity was expected to be lowered by double filling of Ce and Nd, but its further reduction was not significant, due to the similar atomic mass and ionic radius of Ce (140.1 and 0.134 nm) and Nd (144.2 and 0.127 nm).

Figure 7 presents the temperature dependence of the dimensionless figure-of-merit (ZT) for $(\text{Ce}_{1-z}\text{Nd}_z)_y\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. ZT increased with temperature and reached a maximum at temperatures above 723 K due to the onset of intrinsic transition and bipolar conduction. The thermoelectric performance was expected to improve due to the optimized carrier concentration and the enhanced phonon scattering obtained by the charge compensation of Co and the partial double-filling of

Fig. 7. Temperature dependence of the dimensionless figure of merit, ZT, for $(\text{Ce}_{1-z}\text{Nd}_z)_y\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$.

Ce/Nd. The ZT values of the partially filled specimens exhibited significant improvements as compared with those of the completely filled $\text{Ce}_{1-z}\text{Nd}_z\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ specimens. $(\text{Ce}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$ had a ZT_{max} of 0.87 at 723 K while that for $\text{Ce}_{0.25}\text{Nd}_{0.75}\text{Fe}_4\text{Sb}_{12}$ was 0.73 at 723 K [17]. Joo *et al.* [19] reported a ZT_{max} of 0.77 at 723 K for $\text{Ce}_{0.75}\text{Yb}_{0.25}\text{Fe}_3\text{CoSb}_{12}$, and Shin *et al.* [20] reported a ZT_{max} of 0.84 at 723 K for $(\text{Pr}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$. A higher ZT for $(\text{Ce}_{0.75}\text{Nd}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$, at the same temperature, was obtained in the present study. ZT values were improved in the specimens by partial filling and carrier concentration compensation control; however, they were lower than those in other double- or multiple-filled skutterudites [21-24]. Partial double-filling with filler elements having large differences in atomic mass and ionic radius is expected to improve thermoelectric properties.

4. CONCLUSION

Partially double-filled p-type $(\text{Ce}_{1-z}\text{Nd}_z)_y\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ ($z = 0.25$ or 0.75 ; $y = 0.8$; $x = 0, 0.5$ or 1.0) skutterudites were prepared by encapsulated melting, annealing, and hot pressing. All specimens were transformed into the skutterudite phase by heat treatment but a small amount of marcasite phase was also detected. However, void filling with Ce/Nd and Co substitution

can inhibit the formation of the marcasite phase. The partially filled specimens did not exceed the filling fraction limit, which was taken to be $y = 0.8$. Thus, (Ce,Nd)Sb₂ phases were not formed in this study. Both the Seebeck and Hall coefficient values were positive, indicating that all specimens exhibited p-type characteristics. The Seebeck coefficient increased with increasing Co and Nd contents, while the electrical conductivity decreased. In addition, partial filling slightly increased the electrical conductivity but decreased the Seebeck coefficient. The partial double-filling of Ce and Nd could not further reduce the thermal conductivity, compared with the complete double-filling. A maximum dimensionless figure of merit, $ZT_{\max} = 0.87$, was obtained at 723 K for (Ce_{0.75}Nd_{0.25})_{0.8}Fe₃CoSb₁₂.

ACKNOWLEDGMENT

This study was supported by the Civil-Military Technology Cooperation Program, Republic of Korea.

REFERENCES

1. B. C. Scales, D. Mandrus, and R. K. Williams, *Science* **22**, 1325 (1996).
2. D. J. Singh and M. H. Du, *Phys. Rev. B* **82**, 075115 (2010).
3. D. T. Morelli, G. P. Meisner, B. X. Chen, S. Q. Hu, and C. Uher, *Phys. Rev. B* **56**, 7376 (1997).
4. L. D. Chen, T. Kawahara, X. F. Tang, T. Goto, T. Hirai, J. S. Dyck, W. Chen, and C. Uher, *J. Appl. Phys.* **90**, 1864 (2001).
5. X. Shi, J. Yang, J. R. Salvador, M. F. Chi, J. Y. Cho, H. Wang, S. Q. Bai, J. H. Yang, W. Q. Zhang, and L. D. Chen, *J. Am. Chem. Soc.* **133**, 7837 (2011).
6. D. T. Morelli and G. P. Meisner, *J. Appl. Phys.* **77**, 3777 (1995).
7. Q. Li, Z. W. Lin, and J. Zhou, *J. Electron. Mater.* **38**, 1268 (2009).
8. G. Rogl, A. Grytsiv, P. Rogl, E. Bauer, and M. Zehetbauer, *Intermet.* **19**, 546 (2010).
9. G. P. Meisner, D. T. Morelli, S. Hu, J. Yang, and C. Uher, *Phys. Rev. Lett.* **80**, 3551 (1998).
10. G. S. Nolas, J. L. Cohn, and G. A. Slack, *Phys. Rev. B* **58**, 164 (1998).
11. Z. Chen, J. O. Yang, R. H. Liu, L. L. Xi, W. Q. Zhang, and J. Yang, *J. Electron. Mater.* **42**, 2492 (2013).
12. J. Yang, W. Zhang, S. Q. Bai, Z. Mei, and L. D. Chen, *Appl. Phys. Lett.* **90**, 192111 (2007).
13. X. Shi, S. Q. Bai, L. L. Xi, J. O. Yang, W. Q. Zhang, L. D. Chen, and J. Yang, *J. Mater. Res.* **26**, 1745 (2011).
14. G. Rogl, A. Grytsiv, E. Bauer, P. Rogl, and M. Zehetbauer, *Intermet.* **18**, 57 (2010).
15. G. Rogl, A. Grytsiv, M. Falmbigl, E. Bauer, P. Rogl, M. Zehetbauer, and Y. Gelbstein, *J. Alloy. Compd.* **537**, 242 (2012).
16. X. Meng, W. Cai, Z. Liu, J. Li, H. Geng, and J. Sui, *Acta Mater.* **98**, 405 (2015).
17. K. M. Song, D. K. Shin, and I. H. Kim, *J. Kor. Phys. Soc.* **70**, 499 (2017).
18. P. F. Qiu, J. Yang, R. H. Liu, X. Shi, X. Y. Huang, G. J. Snyder, W. Zhang, and L. D. Chen, *J. Appl. Phys.* **109**, 063713 (2011).
19. G. S. Joo, D. K. Shin, and I. H. Kim, *J. Electron. Mater.* **45**, 1251 (2016).
20. D. K. Shin and I. H. Kim, *J. Kor. Phys. Soc.* **69**, 798 (2016).
21. J. Graff, S. Zhu, T. Holgate, J. Peng, J. He, and T. M. Tritt, *J. Electron. Mater.* **40**, 5 (2011).
22. L. Zhou, P. F. Qiu, C. Uher, X. Shi, and L. D. Chen, *Intermet.* **32**, 209 (2013).
23. G. Rogl, A. Grytsiv, P. Rogl, E. Royanian, E. Bauer, J. Horky, D. Setman, E. Schafner, and M. Zehetbauer, *Acta Mater.* **61**, 6778 (2013).
24. G. Rogl, A. Grytsiv, P. Heinrich, E. Bauer, P. Kumar, N. Peranio, O. Eibl, J. Horky, M. Zehetbauer, and P. Rogl, *Acta Mater.* **91**, 227 (2015).