Charge Transport and Thermoelectric Properties of $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ Skutterudites

Ye-Eun Cha and Il-Ho Kim*

Department of Materials Science and Engineering, Korea National University of Transportation, Chungju 27469, Republic of Korea

Abstract: Partially La/Pr-double-filled and Co-substituted $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ skutterudites were synthesized by encapsulated melting and vacuum hot pressing. $(\text{La},\text{Pr})\text{Sb}_2$ phases were not formed because the partial filling did not exceed the filling fraction limit, and the amount of secondary phase FeSb_2 also decreased as the Co content increased. Electrical conductivity decreased with increasing Pr filling and Co substitution because of the decreased carrier concentration. The $(\text{La}_{0.75}\text{Pr}_{0.25})_{0.8}\text{Fe}_4\text{Sb}_{12}$ skutterudite, which was not charge-compensated with Co, showed the highest electrical conductivity of $2.44 \times 10^5 \text{ Sm}^{-1}$ at 323 K. In contrast, the Seebeck coefficient increased with increased Co substitution, and the $(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_3\text{CoSb}_{12}$ exhibited the maximum Seebeck coefficient of $168.2 \mu\text{VK}^{-1}$ at 723 K; $(\text{La}_{0.75}\text{Pr}_{0.25})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$ exhibited the highest power factor of $2.67 \text{ mW m}^{-1} \text{ K}^{-2}$ at 823 K; and $(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_3\text{CoSb}_{12}$ exhibited the lowest thermal conductivity of $2.09 \text{ W m}^{-1} \text{ K}^{-1}$ at 523 K. Consequently, $(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$ exhibited the maximum dimensionless figure of merit, $ZT = 0.79$ at 723 K.

(Received August 13, 2018; Accepted August 27, 2018)

Keywords: thermoelectric, skutterudite, partial double filling, charge compensation

1. INTRODUCTION

Thermoelectric devices convert thermal energy into electrical energy directly and reversibly. The performance of thermoelectric materials is determined by a dimensionless figure of merit, $ZT = \alpha^2 \sigma T \kappa^{-1}$, where α is the Seebeck coefficient, σ is the electrical conductivity, T is the absolute temperature, and κ is the thermal conductivity [1]. To obtain higher ZT values, thermoelectric materials should have a high Seebeck coefficient, high electrical conductivity, and low thermal conductivity. However, the Seebeck coefficient and the electrical conductivity have a trade-off relationship with carrier concentration. In addition, it is difficult to control each parameter independently, because the thermal conductivity increases as the electrical conductivity increases [2,3]. The requirements for good thermoelectric performance are described by the phonon-glass and electron-crystal (PGEC) concept proposed by Slack [4]. The conditions for obtaining high ZT values include a complex structure with a

large unit cell, strong atomic bonds, large atomic masses, high carrier mobility, narrow bandgap energy, and low thermal conductivity. Skutterudite satisfies these criteria except for the low thermal conductivity condition [4].

Skutterudite has the basic form of 8MX_3 (M: transition metal and X: pnictogen element) and two large voids in the unit cell. Thermal conductivity can be reduced by filling heavy atoms (fillers or rattlers) into the voids. The phonon scattering is enhanced by the rattling effect of lattice vibrations in the void. Therefore, the lattice thermal conductivity can be reduced and the thermoelectric performance can be improved [5,6]. Such filled skutterudites have the chemical formula RM_4X_{12} (R: alkali, alkaline-earth, or rare-earth metal). The CoSb_3 -based n-type filled skutterudite is used in the form $\text{R}_z\text{Co}_4\text{Sb}_{12}$ [5-8], and the FeSb_3 -based p-type filled skutterudite is used in the form $\text{R}_z\text{Fe}_4\text{Sb}_{12}$ [9-11]. The n-type $\text{Co}_4\text{Sb}_{12}$ skutterudite is stable with 72 valence electrons, but the p-type $\text{Fe}_4\text{Sb}_{12}$ skutterudite is unstable because it has only 68 valence electrons. Therefore, excess electrons are required for stabilization [11]. Phase stabilization with the $\text{R}^{4+}[\text{Fe}_4\text{Sb}_{12}]^{4-}$ form is possible by filling the void, but most of the elements used as fillers exist

*Corresponding Author: Il-Ho Kim
[Tel: +82-43-841-5387, E-mail: ihkim@ut.ac.kr]
Copyright © The Korean Institute of Metals and Materials

as valences of R^{2+} and R^{3+} . As a result, the valence electrons are absent when filling these elements [12]. Thus, charge compensation is needed, and fulfilled by substituting Co or Ni for the Fe site. In addition, p-type skutterudites show lower thermal conductivities than n-type skutterudites, but owing to their low charge transport and electrical properties, they exhibit lower ZT values than those of n-type skutterudites [13]. Therefore, it is necessary to improve the thermoelectric performance of p-type skutterudites.

Filling the voids in a skutterudite structure is a very effective method of reducing the lattice thermal conductivity, because each filler atom has a specific resonant frequency and acts as a phonon scattering center [5,8,14,15]. If two or more kinds of rare-earth elements with heavier atomic masses are filled, the lattice thermal conductivity can be further reduced owing to the broader spectrum of phonon frequencies [5,6,9]. Thus, double- or multiple-filling can cause more phonon scattering, resulting in improved thermoelectric performance with a lower lattice thermal conductivity [6,15-17]. Recently, some studies have reported that p-type skutterudites cannot be completely filled when the charge compensation is performed by substituting Co or Ni at the Fe site [18-20]. In our previous study, La/Pr double-filled and Co-substituted skutterudites exhibited $(La,Pr)Sb_2$ secondary phases because the La/Pr double filling exceeded the filling fraction limit (FFL) [21]. In this study, La/Pr-partially-double-filled and Co-substituted $(La_{1-z}Pr_z)_yFe_{4-x}Co_xSb_{12}$ were prepared, and their thermoelectric and charge transport properties were examined.

2. EXPERIMENTAL PROCEDURE

La (purity 99.9%, Kojundo), Pr (purity 99.9%, Kojundo), Fe (purity 99.95%, Cerac), Co (purity 99.95%, Alfa Aesar), and Sb (purity 99.999%, LTS) were combined according to the stoichiometry of $(La_{1-z}Pr_z)_{0.8}Fe_{4-x}Co_xSb_{12}$, melted at 1323 K for 10 h using encapsulated melting, and then quenched in water. The ingot was annealed at 873 K for 24 h in an evacuated quartz ampoule, and ground to powder with particle diameters less than 75 μm . The synthesized powder was charged into a graphite mold with an inner diameter of 10 mm and hot pressed with 70 MPa of applied pressure at 898 K for 1 h in a vacuum.

Phase and lattice constants were analyzed by X-ray diffraction (XRD: Bruker, D8 Advance) with Cu K_α (40 kV and 30 mA) radiation. Diffraction peaks were measured in $q-2\theta$ mode ($2\theta = 10^\circ$ to 90°) with a step size of 0.02° , a scan speed of 0.4 s/step, and a wavelength of 0.15405 nm. The microstructures were observed by scanning electron microscopy (SEM, FEI, Quanta 400), and the chemical compositions were analyzed by energy-dispersive spectroscopy (EDS: Bruker, Quantax 200). The sintered specimens were cut into rectangular pieces with dimensions of $3 \times 3 \times 9 \text{ mm}^3$ to measure both the Seebeck coefficient (α) and the electrical conductivity (σ), which were measured by a DC 4-probe method with the ZEM-3 (Ulvac-Riko) equipment. The hot-pressed specimens were also cut into discs with dimensions of 10 (diameter) $\times$ 1 mm^2 (thickness) to measure both the thermal conductivity (κ) and the Hall effect. The thermal conductivity ($\kappa = Dc_p d$) was evaluated by measuring the thermal diffusivity (D), specific heat (c_p), and density (d) using the laser flash method with the TC-9000H (Ulvac-Riko) equipment. The Hall coefficient, carrier concentration, and mobility were measured using a Keithley 7065 system at room temperature with a constant magnetic field (1 T) and current (50 mA). The power factor ($PF = \alpha^2 \sigma$) and the dimensionless figure of merit ($ZT = \alpha^2 \sigma T \kappa^{-1}$) were evaluated using the measured Seebeck coefficient and electrical conductivity and the calculated thermal conductivity.

3. RESULTS AND DISCUSSION

Figure 1 shows the XRD patterns of $(La_{1-z}Pr_z)_{0.8}Fe_{4-x}Co_xSb_{12}$. The diffraction peaks of all specimens correspond to the standard data for the skutterudite phase (PDF# 56-1123, space group: $Im\bar{3}$), and a small amount of the marcasite ($FeSb_2$) phase (PDF# 70-3985, space group: $Pnnm$) was also identified. The diffraction peaks for the marcasite phase between 31.9° and 32.1° are enlarged in Fig. 1(b) and 1(c); intensities decreased with increasing Co content. This resulted from the stabilized skutterudite phase due to charge compensation by Co substitution. The diffraction peaks shifted to higher angles, which was attributed to a decrease in the lattice constant because the atomic radius of Co (0.167 nm) is smaller than that of Fe (0.172 nm).

Fig. 1. XRD patterns of (a) the $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ skutterudites and enlarged XRD patterns of the specimens with (b) $z = 0.25$ and (c) $z = 0.75$.

Figure 2 shows the SEM images and EDS line scans of $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. The FeSb_2 phase (dark region) was formed with the skutterudite phase (bright region), but the formation of the FeSb_2 phase was inhibited with increasing Co content. In our previous study, $(\text{La},\text{Pr})\text{Sb}_2$ phases were observed in the fully-filled $\text{La}_{1-z}\text{Pr}_z\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ specimens, exceeding the FFL [21]. However, in the present study, the partially-filled $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ skutterudites did not produce $(\text{La},\text{Pr})\text{Sb}_2$ secondary phases. Therefore, it was confirmed that the $(\text{La},\text{Pr})\text{Sb}_2$ phase was not formed when the partial filling did not exceed the FFL.

Table 1 shows the chemical compositions, relative densities, lattice constants, and charge transport properties of $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. The actual compositions showed no significant differences from the nominal compositions after the synthesis, annealing, and sintering, thus the processes and conditions of sample preparation were reasonable. All specimens showed a relative density higher than 98.5% of the theoretical density. The calculated lattice constants ranged from 0.9117 to 0.9133 nm according to the La/Pr filling ratio and Co substitution amount. Because the atomic radius of Co (0.167 nm) is smaller than Fe (0.172 nm), the lattice constant decreased with increasing Co substitution. In addition, because Pr (0.133 nm) is smaller than La (0.136 nm), the lattice constant further decreased with increasing Pr filling [22,23]. All specimens showed

Fig. 2. SEM images and EDS line scans of $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$.

Table 1. Chemical compositions, relative densities, lattice constants, and charge transport properties of $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ at room temperature.

Composition		Relative Density [%]	Lattice Constant [nm]	Hall Coefficient [$10^{-3} \text{ cm}^3 \text{ C}^{-1}$]	Carrier Mobility [$\text{cm}^2 \text{ V}^{-1} \text{ s}^{-1}$]	Carrier Concentration [10^{21} cm^{-3}]
Nominal	Actual					
$(\text{La}_{0.75}\text{Pr}_{0.25})_{0.8}\text{Fe}_4\text{Sb}_{12}$	$\text{La}_{0.56}\text{Pr}_{0.18}\text{Fe}_{4.10}\text{Sb}_{11.96}$	98.74	0.9133	1.74	4.25	3.59
$(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_4\text{Sb}_{12}$	$\text{La}_{0.19}\text{Pr}_{0.55}\text{Fe}_{4.11}\text{Sb}_{11.95}$	98.75	0.9131	1.81	4.36	3.45
$(\text{La}_{0.75}\text{Pr}_{0.25})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$	$\text{La}_{0.57}\text{Pr}_{0.19}\text{Fe}_{3.58}\text{Co}_{0.49}\text{Sb}_{11.97}$	98.54	0.9126	2.63	4.97	2.37
$(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$	$\text{La}_{0.19}\text{Pr}_{0.54}\text{Fe}_{3.58}\text{Co}_{0.52}\text{Sb}_{11.97}$	99.01	0.9123	2.98	5.45	2.09
$(\text{La}_{0.75}\text{Pr}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$	$\text{La}_{0.57}\text{Pr}_{0.18}\text{Fe}_{3.04}\text{Co}_{1.06}\text{Sb}_{11.95}$	99.13	0.9120	5.61	6.77	1.11
$(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_3\text{CoSb}_{12}$	$\text{La}_{0.16}\text{Pr}_{0.53}\text{Fe}_{3.09}\text{Co}_{1.08}\text{Sb}_{11.94}$	99.06	0.9117	5.79	6.96	1.08

positive Hall coefficients, indicating p-type conduction by the majority charge carriers of holes. The carrier concentrations ranged from 1.08×10^{21} to $3.59 \times 10^{21} \text{ cm}^{-3}$, which decreased with increasing Co and Pr contents. This decrease in the carrier concentration was due to the charge compensation induced by substituting Co for Fe and to the differences in valence states of La^{3+} and $\text{Pr}^{3+/4+}$. The carrier mobility varied inversely with the carrier concentration, which was a general behavior due to ionized impurity scattering.

Figure 3 shows the temperature dependence of the electrical conductivity for $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. The electrical conductivity decreased with increasing temperature, indicating that the specimens were degenerate semiconductors. The electrical conductivity decreased as the content of Co increased at constant temperature. As shown in Table 1, this was due to the decreased carrier concentration caused by charge compensation. The change in the electrical conductivity with the La/Pr filling ratio was not significant. The electrical conductivities ranged from 1.20×10^5 to $2.44 \times 10^5 \text{ Sm}^{-1}$ at 323 K, while the fully-filled specimens showed electrical conductivities from 1.26×10^5 to $2.33 \times 10^5 \text{ Sm}^{-1}$ at 323 K [21]. The $(\text{La}_{0.75}\text{Pr}_{0.25})_{0.8}\text{Fe}_4\text{Sb}_{12}$ sample showed the highest electrical conductivity of $2.44 \times 10^5 \text{ Sm}^{-1}$ at 323 K.

Figure 3 shows the temperature dependence of the Seebeck coefficient for $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. All specimens showed positive Seebeck coefficients, reconfirming p-type conduction. The Seebeck coefficient increased with increasing temperature, and it further increased with increasing Co and Pr contents. The Seebeck coefficient can be expressed as $\alpha = (8/3)\pi^2 k_B^2 m^* \text{Te}^{-1} h^{-1} (\pi/3p)^{2/3}$, where k_B is the Boltzmann constant, m^* is the effective carrier mass, e is the electronic charge, h is the Planck constant, and p is the

Fig. 3. Temperature dependence of the electrical conductivity for $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. **Fig. 4.** Temperature dependence of the Seebeck coefficient for $(\text{La}_{1-z}\text{Pr}_z)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$.

carrier concentration. Thus, from the relation between the Seebeck coefficient and the carrier concentration, the

Fig. 5. Temperature dependence of the power factor for $(\text{La}_{1-x}\text{Pr}_x)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$.

Seebeck coefficient decreased as the carrier concentration decreased with increasing Pr filling and Co substitution. As the temperature increased, the Seebeck coefficient showed a peak value because the carrier concentration increased dramatically owing to the intrinsic transition above a specific temperature. Therefore, the maximum value was observed between 723 and 823 K. The temperature for the intrinsic transition shifted to lower temperatures with increasing charge compensation of Co. The $(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_3\text{CoSb}_{12}$ showed the highest Seebeck coefficient of $168.2 \mu\text{V K}^{-1}$ at 723 K, which was higher than the value of $158.7 \mu\text{V K}^{-1}$ at 723 K for the fully-filled $\text{La}_{0.75}\text{Pr}_{0.25}\text{Fe}_3\text{CoSb}_{12}$ [21]. This was attributed to a lower carrier concentration caused by partial filling.

Figure 5 shows the temperature dependence of the power factor (PF) for $(\text{La}_{1-x}\text{Pr}_x)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. The PF increased with increasing temperature, and a maximum PF was found between 723 and 823 K owing to the trade-off relationship between the Seebeck coefficient and the electrical conductivity. However, the PF did not change significantly with the La/Pr filling ratio. The PF ranged from 1.45 to $2.62 \text{ mW m}^{-1} \text{ K}^{-2}$ at 323 K, and the $(\text{La}_{0.75}\text{Pr}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$ showed the highest PF of $2.67 \text{ mW m}^{-1} \text{ K}^{-2}$ at 823 K. The fully-filled specimens showed PF values ranging from 1.19 to $1.61 \text{ mW m}^{-1} \text{ K}^{-2}$ at 323 K, which were lower than those of the partially-filled specimens. However, the fully-filled $\text{La}_{0.75}\text{Pr}_{0.25}\text{Fe}_3\text{CoSb}_{12}$ showed the highest PF of 3.17 mW m^{-1}

Fig. 6. Temperature dependence of the thermal conductivity of $(\text{La}_{1-x}\text{Pr}_x)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$: (a) total thermal conductivity, (b) electronic thermal conductivity, and (c) lattice thermal conductivity.

K^{-2} at 823 K [21], which was higher than those of the partially-filled specimens. Unlike the fully-filled specimens, the maximum PF was obtained for the $x = 0.5$ substitution, which was attributed to the optimal carrier concentration.

Figure 6 shows the temperature dependence of the thermal conductivity for $(\text{La}_{1-x}\text{Pr}_x)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. The thermal conductivity (κ) is the sum of the lattice thermal conductivity (κ_L) and the electronic thermal conductivity (κ_E), which can be separated using the Wiedemann-Franz law ($\kappa_E = L\sigma T$), where L is the Lorenz number, taken as $2.0 \times 10^{-8} \text{ V}^2 \text{ K}^{-2}$ in

this study [24]. As shown in Fig. 6(a), the change in thermal conductivity was more dominantly attributed to the Co content than the La/Pr filling ratio. The thermal conductivity decreased with increasing Co substitution, and the values of $\kappa = 2.09 - 3.78 \text{ W m}^{-1} \text{ K}^{-1}$ were observed in the measured temperature range. The thermal conductivity increased at temperatures above 623 K owing to the bipolar effect. The fully-filled $\text{La}_{1-x}\text{Pr}_x\text{Fe}_{1-x}\text{Co}_x\text{Sb}_{12}$ showed values of $\kappa = 2.18 - 3.10 \text{ W m}^{-1} \text{ K}^{-1}$ at temperatures between 323 and 823 K [21]. The $(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_3\text{CoSb}_{12}$ showed the lowest κ of $2.09 \text{ W m}^{-1} \text{ K}^{-1}$ at 323 K, while the fully-filled $\text{La}_{0.25}\text{Pr}_{0.75}\text{Fe}_3\text{CoSb}_{12}$ showed the lowest κ of $2.18 \text{ W m}^{-1} \text{ K}^{-1}$ at 323 K, which was slightly higher than the κ of partially-filled $(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_3\text{CoSb}_{12}$. As shown in Fig. 6(b), the electronic thermal conductivity decreased with increasing Co substitution owing to the decreased carrier concentration caused by charge compensation. The $(\text{La}_{0.75}\text{Pr}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$ sample showed the lowest κ_E of $0.74 \text{ W m}^{-1} \text{ K}^{-1}$ at 323 K. The fully-filled $\text{La}_{1-x}\text{Pr}_x\text{Fe}_{1-x}\text{Co}_x\text{Sb}_{12}$ specimens showed higher values of $\kappa_E = 1.01 - 2.55 \text{ W m}^{-1} \text{ K}^{-1}$ [21] than the partially-filled specimens at all temperatures. As shown in Fig. 6(c), the values of $\kappa_L = 1.01 - 1.51 \text{ W m}^{-1} \text{ K}^{-1}$ were obtained at 623 K, which were the lowest lattice thermal conductivities of all the specimens. The lattice thermal conductivity decreased with increasing phonon scattering owing to impurity (alloy) scattering in the Co-substituted specimens, but the change in the lattice thermal conductivity caused by the filling ratio of La/Pr was small. The $(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$ showed the lowest κ_L of $1.01 \text{ W m}^{-1} \text{ K}^{-1}$ at 623 K. The fully-filled $\text{La}_{1-x}\text{Pr}_x\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$ specimens showed the lowest κ_L at temperatures between 623 and 723 K, and $\text{La}_{0.25}\text{Pr}_{0.75}\text{Fe}_4\text{Sb}_{12}$ showed the lowest κ_L of $0.33 \text{ W m}^{-1} \text{ K}^{-1}$ at 723 K [21]. Compared to the fully-filled specimens, relatively higher κ_L values were obtained for the partially-filled specimens. Filled skutterudites have been reported to be effective at improving phonon scattering as a result of low resonance frequency scattering due to heavy filler elements or small ionic radii of filler elements [15-22]. It was expected that the lattice thermal conductivity would be reduced by improving the phonon scattering using La and Pr as the filler elements, which are heavy and have small ionic radii. As mentioned above, the enhancement of the phonon scattering due to the similar atomic and ionic radii of La and Pr was insignificant compared with the complete double filling.

Fig. 7. Temperature dependence of the dimensionless figure of merit, ZT, for $(\text{La}_{1-x}\text{Pr}_x)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$.

Figure 7 shows the temperature dependence of the dimensionless figure of merit (ZT) for $(\text{La}_{1-x}\text{Pr}_x)_{0.8}\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. ZT increased with temperature, and maximum ZT values were obtained at temperatures between 723 and 823 K for the Co-substituted specimens. The $(\text{La}_{0.25}\text{Pr}_{0.75})_{0.8}\text{Fe}_{3.5}\text{Co}_{0.5}\text{Sb}_{12}$ showed the maximum ZT = 0.79 at 723 K. However, the fully-filled $\text{La}_{0.75}\text{Pr}_{0.25}\text{Fe}_4\text{Sb}_{12}$ showed the maximum ZT = 0.83 at 823 K. In this study, La and Pr were used as filling elements for partial-double filling, and the carrier concentration optimization and the phonon scattering were expected to be enhanced by Co charge compensation. In addition, the improvement in phonon scattering was intended to improve thermoelectric performance by reducing the lattice thermal conductivity. However, the atomic mass and ionic radius were 138.9 and 0.136 nm for La and 140.9 and 0.133 nm for Pr, respectively; therefore, the differences in the atomic masses and ionic radii of La and Pr were not sufficient to cause a significant change in the lattice thermal conductivity as the La-to-Pr filling ratio was varied. At the same time, the improvement in phonon scattering by partial-double filling was found to be insignificant, due to the very similar ionic radii and atomic masses of La and Pr. Therefore, the thermoelectric performance was not improved, compared to $\text{La}_{1-x}\text{Pr}_x\text{Fe}_{4-x}\text{Co}_x\text{Sb}_{12}$. In addition, Shin *et al.* [25] reported a $ZT_{\text{max}} = 0.85$ at 723 K for $(\text{Pr}_{0.75}\text{Yb}_{0.25})_{0.8}\text{Fe}_3\text{CoSb}_{12}$, Zhou *et al.* [26] reported a $ZT_{\text{max}} = 0.99$ at 700 K for $\text{Yb}_{0.25}\text{La}_{0.60}\text{Fe}_{2.7}\text{Co}_{1.3}\text{Sb}_{12}$, and Rogl *et*

al. [27] reported a $ZT_{\max} = 1.3$ at 825 K for $DD_{0.6}Fe_3CoSb_{12}$, where DD is didymium. In this study, when the Co was charge-compensated, the temperature range of the $ZT_{\max}$ shifted to lower temperatures, and thus applications for thermoelectric generation in the intermediate temperature range, were expected.

4. CONCLUSIONS

Partially double-filled p-type $(La_{1-z}Pr_z)_yFe_{4-x}Co_xSb_{12}$ ($z = 0.25, 0.75$; $y = 0.8$; $x = 0, 0.5, 1.0$) skutterudites were synthesized by encapsulated melting and sintered by hot pressing. All specimens were transformed into the skutterudite phase by annealing, but the marcasite phase was also formed. However, $(La,Pr)Sb_2$ phases were not produced and the amount of $FeSb_2$ was significantly reduced by La/Pr partial filling and Co substitution. The Hall coefficient and the Seebeck coefficient values were positive, indicating that all specimens had p-type conduction characteristics. The Seebeck coefficient increased with increased Pr and Co contents, while the electrical conductivity decreased due to the decreased carrier concentration. Compared with the fully-filled specimens, the partially-filled specimens showed slightly lower Seebeck coefficients and higher electrical conductivities due to the increased carrier concentration caused by partially filling. The partial double filling of La and Pr led to a higher lattice thermal conductivity. The maximum ZT value of 0.79 was obtained at 723 K for the $(La_{0.25}Pr_{0.75})_{0.8}Fe_{3.5}Co_{0.5}Sb_{12}$.

REFERENCES

1. L. D. Zhao, V. P. Dravid, and M. G. Kanatzidis, *Energy Environ. Sci.* **7**, 251 (2014).
2. T. Caillat, A. Borshchevsky, and J. P. Fleurial, *J. Appl. Phys.* **80**, 4442 (1996).
3. C. Sales, D. Mandrus, B. C. Chakomakos, V. Keppens, and J. R. Thompson, *Phys. Rev. B* **56**, 15081 (1997).
4. G. A. Slack, *Handbook of Thermoelectricity*, edited by D. M. Rowe, p. 407, CRC, Boca Raton (1995).
5. L. D. Chen, T. Kawahara, X. F. Tang, T. Goto, T. Hirai, J. S. Dyck, W. Chen, and C. Uher, *J. Appl. Phys.* **90**, 1864 (2001).
6. X. Shi, J. Yang, J. R. Salvador, M. F. Chi, J. Y. Cho, H. Wang, S. Q. Bai, J. H. Yang, W. Q. Zhang, and L. D. Chen, *J. Am. Chem. Soc.* **133**, 7837 (2011).
7. D. T. Morelli, G. P. Meisner, B. X. Chen, S. Q. Hu, and C. Uher, *Phys. Rev. B* **56**, 7376 (1997).
8. D. T. Morelli and G. P. Meisner, *J. Appl. Phys.* **77**, 3777 (1995).
9. Q. Li, Z. W. Lin, and J. Zhou, *J. Electron. Mater.* **38**, 1268 (2009).
10. G. Rogl, A. Grytsiv, P. Rogl, E. Bauer, and M. Zehetbauer, *Intermet.* **19**, 546 (2010).
11. G. P. Meisner, D. T. Morelli, S. Hu, J. Yang, and C. Uher, *Phys. Rev. Lett.* **80**, 3551 (1998).
12. B. X. Chen, J. H. Xu, C. Uher, D. T. Morelli, G. P. Meisner, J. P. Fleurial, T. Caillat, and A. Borshchevsky, *Phys. Rev. B* **55**, 1476 (1997).
13. S. Ballikaya, N. Uzar, S. Yildirim, H. Chi, X. L. Su, G. J. Tan, X. F. Tang, and C. Uher, *J. Electron. Mater.* **42**, 1622 (2013).
14. G. S. Nolas, J. L. Cohn, and G. A. Slack, *Phys. Rev. B* **58**, 164 (1998).
15. Z. Chen, J. O. Yang, R. H. Liu, L. L. Xi, W. Q. Zhang, and J. Yang, *J. Electron. Mater.* **42**, 2492 (2013).
16. J. Yang, W. Zhang, S. Q. Bai, Z. Mei, and L. D. Chen, *Appl. Phys. Lett.* **90**, 192111 (2007).
17. X. Shi, S. Q. Bai, L. L. Xi, J. O. Yang, W. Q. Zhang, L. D. Chen, and J. Yang, *J. Mater. Res.* **26**, 1745 (2011).
18. G. Rogl, A. Grytsiv, E. Bauer, P. Rogl, and M. Zehetbauer, *Intermet.* **18**, 57 (2010).
19. Y. E. Cha and I. H. Kim, *Korean J. Met. Mater.* **56**, 465 (2018).
20. X. Meng, W. Cai, Z. Liu, J. Li, H. Geng, and J. Sui, *Acta Mater.* **98**, 405 (2015).
21. K. M. Song, D. K. Shin, and I. H. Kim, *J. Electron. Mater.* **45**, 1227 (2016).
22. P. F. Qiu, J. Yang, R. H. Liu, X. Shi, X. Y. Huang, G. J. Snyder, W. Zhang, and L. D. Chen, *J. Appl. Phys.* **109**, 063713 (2011).
23. R. D. Shannon, *Acta Cryst. A* **32**, 751 (1976).
24. C. Kittel, *Introduction to Solid State Physics*, 6th ed., p. 152, Wiley, New York (1986).
25. D. K. Shin and I. H. Kim, *J. Korean Phys. Soc.* **70**, 591 (2017).
26. L. Zhou, P. F. Qiu, C. Uher, X. Shi, and L. D. Chen, *Intermet.* **32**, 209 (2013).
27. G. Rogl, A. Grytsiv, P. Rogl, E. Royanian, E. Bauer, J. Horky, D. Setman, E. Schafner, and M. Zehetbauer, *Acta Mater.* **61**, 6778 (2013).